

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-180360

(43)Date of publication of application : 12.07.1996

(51)Int.Cl. G11B 5/66

(21)Application number : 06-317951

(71)Applicant : HITACHI LTD

(22)Date of filing : 21.12.1994


(72)Inventor : NAKAMURA ATSUSHI
FUTAMOTO MASAOKI
HIRAYAMA YOSHIYUKI
TAKAYAMA TAKANOBU

(54) PERPENDICULAR MAGNETIC RECORDING MEDIUM AND MAGNETIC RECORDER

(57)Abstract:

PURPOSE: To provide a medium excellent in crystal orienting property and having high perpendicular magnetic anisotropy by forming an under film with a Co-Ru alloy.

CONSTITUTION: A Co-Ru alloy forms a solid soln. over the entire compsn. range at ordinary temp. and the crystal structure is a hexagonal close-packed structure. An under film 12 of the Co-Ru alloy is formed on a nonmagnetic substrate 11 such as a glass substrate or an NiP coated Al alloy substrate. In the film 12, (0001) faces become parallel to the substrate and c-axes are liable to orient perpendicularly. A perpendicularly magnetized film 13 of a Co-based alloy and a protective film 14 are then formed on the film 12 to obtain the objective perpendicular magnetic recording medium. The proper concn. of Ru is $\geq 40\text{at.}\%$ because a compsn. having $\geq 40\text{at.}\%$ concn. of Ru gives $\leq 0^\circ$ C Curie temp.



LEGAL STATUS

[Date of request for examination] 15.03.2000

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3345199

[Date of registration] 30.08.2002

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office